

ATLAS RIB

Method of Manufacture	Needle Punch Rib
Pile Fibre/Yarn	100% Polypropylene
Pile Weight	600 gms
Backing	Gelfoam - Water resistant
Total Weight	1170 gms
Availability	4m Gel Back 2m Fibre Bonded
No. Of Colours	10
Flammability	BS 4790-1987 (1996) Hot Metal Nut method When fully adhered <30mm Low
Abrasion	BS EN 1963 - Test A 1998 Lisson Tretrad Test Class 4. contract Locations.
Colour Fastness	BS 1006/ To Light 6+ To Shampoo 4-5 Wet Rubbing 4-5 Dry Rubbing 4-5
PLEASE NOTE:	For technical reasons, as with all textile materials it is not possible to colour match from different batches. Orders that need to colour match should be placed at the same time. Production may therefore show variations to the sample card.